


AA252

Ceramic Stair Nosing

Image/
Drawing

Description

Natural Satin anodised aluminium maximum safety stair nosing profile for ceramic tile covered stairs. With a special blend of P.V.C. and sustainably sourced industrial sand, giving a homogeneous hard wearing anti-slip flooring for wet and dry conditions.

Purpose

This product has been designed to provide a retrofitted, neat and safe step edge for ceramic tiles and other flooring.

Material

- Anodised Aluminium
- Standard 3.66 Metre Lengths
- Supplied pre drilled for countersunk screw fixing (screws supplied)

Insert

2 x 13mm Tredsafe Diamondtred Insert



Insert

Special properties

Tredsafe's Diamondtred insert is resistant to attack from ultraviolet light, oil, grease, petrol, salt, dilute acids on alkalis, common household chemicals and detergents. Organic solvents will soften the Diamondtred insert.

Fields of application

Suitable for interior or exterior use

Slip Resistance**AS/NZS 4586 - 2013**

Wet Pendulum – mean 47 – class P4

Dry Floor – mean 0.75 – class D1

Wet/Barefoot ramp – Result 30° – class C

Oil – Wet Ramp – Result 21° – class R11

AS/NZS 3661.1:1993

Dry (tortus): 0.80

Wet (pendulum): 0.44

BS 7976:2002

Pendulum test - dry | PTV average 57

Pendulum test - wet | PTV average 47

DIN 51130:2010

Inclined platform test: R11

Flammability and smoke density**AS1530.3.1982**

Flame Spread = 0 Smoke Dev = 7

AS/ISO 9239.1 2010

Mean Critical Radiant Flux 10.3kw/m²

Mean smoke development rate 85
percentage minutes

Insert

Description		Values
Residual indentation	2.5mm dial guage	Mean 0.05mm
Dimensional stability 80°C 6 hours		0.12%
Moisture movement 23°C 24 hours		0.02%
Elastic property Tensile strength		2.48mj/m3
Heat Ageing 70°C for 15 days	Exudation Colour change	None None
Wear Resistance Taber Abraser	1kg load H18 wheel @ 60rpm	1000 revs 0.6m weight loss

Information given in this data sheet is based on the current state of knowledge. This does not exempt the purchaser from carrying out his own careful inspections of incoming goods and their suitability for local building codes. We reserve the right to make changes to the product data in the course of technical progress or due to operationally related further development. Owing to factors beyond our control during application, recommendations given in this data sheet require tests and experiments by the customer. Our recommendations do not exempt the customer from the obligation to check any infringements of third-party rights himself and eliminate them if necessary. The suggestions for product use are not equivalent to a warranty of its suitability for the recommended purpose.

Each new release of this data sheet supersedes the previous one.

Release: June 2025